



# Sanded Stucco

**A pre-blended sanded stucco designed for exterior grade construction. Conforms to appropriate sections of ASTM C 926 for application of Portland cement based plaster. No chloride accelerators are used in the mix and all components are compatible with reinforcing steel. Ideal for new construction, restoration and repair of concrete block or brick and patching.**

## **SAFETY:**

READ and UNDERSTAND the Material Safety Data Sheet (MSDS) before using this products. WARNING: Wear protective clothing and equipment. See HMIS block. For emergency information, call CHEMTREC at 800-424-9300 or 703-527-3887 (outside USA). KEEP OUT OF REACH OF CHILDREN.

## **PREPARATION:**

Remove all unsound concrete, mortar, grease, oil, paint and other foreign materials that will inhibit performance.

## **MIXING:**

Use clean tools and potable water. Use approximately 1-1/2 gallons of water per 80 lb. bag. Mix only quantities that can be applied in one hour.

Place the water in the mixing container and gradually add the SAKRETE® Sanded Stucco to the mixing water and mix until material is wet and of a trowelable consistency. Water and mixing time must be kept to a minimum and be consistent between batches to reduce the possibility of variations in color. Wash out the mixer periodically to keep material from caking. If the mixture becomes stiff and difficult to trowel, discard it. When using multiple batches of SAKRETE® Sanded Stucco, combine bags from different lots to promote uniform color. Refer to applicable sections of the standards referenced. DO NOT re-temper. Re-tempering will seriously affect color.

## **PLACEMENT:**

1. Apply over clean, reinforced substrate, which has a properly installed flashing.
2. Scratch and brown coat to a minimum thickness of 3/4" for a single coat application.

## **CURING:**

Excessive water used in curing will affect finish color and performance. Protect newly applied substrates from rain for 12 hours. Protect from freezing for 48 hours after application. Under such conditions, if not modified, lightly fog spray. Cure per ACI 308 - Standard Practice for Curing Concrete. As with all stucco, surface cracking may occur due to curing conditions, control joint configurations, over-watering, over-troweling or other conditions beyond the control of the manufacturers of SAKRETE® products. Efflorescence is a naturally occurring phenomenon associated with Portland cement based products. Elevated mineral content, salts or other particulates can exacerbate this condition.

## **STORAGE:**

Store in a tightly closed container off the floor in a dry place.

## **COVERAGE:**

One 80 lb. bag will yield approximately 11 ft<sup>2</sup> at 3/4" thick, 20 ft<sup>2</sup> at 1/2" thick.

## **PACKAGING:**

80 lb. bag (36.2 kg) - UPC: 7-64661-20480-0

The Pro's Choice Since 1936



# Sanded Stucco

## ENVIRONMENTAL ADVISORY:

Uncured or crushed cured cement is an environmental hazard, which may adversely affect fish and wildlife. Dispose of construction debris containing cement, including empty bags, at a permitted municipal disposal firm. Do not use crushed concrete as a fill near an aquatic habitat.

### HMIS BLOCK

#### CONCRETE MIX

HEALTH	1
FLAMMABILITY	0
REACTIVITY	0
PERSONAL PROTECTION	X

**WARNING! CAUSES IRRITATION** - Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Exposure may result in irritation of the skin, eyes or nasal passages from alkali in Portland cement. When wet, contact with the skin or eyes may result in irritation or burns.

**FIRST AID:** In case of eye contact, flush immediately with plenty of water. If irritation persists, get medical attention. **WARNING! HARMFUL IF INHALED** - Avoid breathing dust. Keep container closed. Use adequate ventilation. Excessive exposure by inhalation over an extended period of time may result in the development of pulmonary diseases including pneumoconiosis and silicosis. Crystalline Silica has been classified by IARC and NTP as a carcinogen.

## LIMITED PRODUCT WARRANTY

US MIX Co. (Manufacturer) warrants to Buyer that this product at the time and place of shipment is of good quality and conforms to manufacturers' specifications in force on the date of manufacture when used in accordance with the instructions hereon. Manufacturer cannot warrant or guarantee any particular method of use, application or performance of the product under any particular condition. This limited warranty cannot be extended or amended by manufactures' salespeople, distributors, or representatives or by any sales information, specifications of anyone other than manufacturer. Liability under this warranty is expressly limited to refund of the purchase price.

US MIX Co.  
800-397-9903  
303-778-7227  
[www.usmix.com](http://www.usmix.com)